



Stainless Steel 17-4

DIRECT METAL LASER SINTERING MATERIAL SPECIFICATIONS

Highlights

- Pre-alloyed, precipitation hardenable stainless steel
- Good welding and machining characteristics
- Good mechanical properties

Applications

- Parts requiring post-production processing
- Oil and gas industry
- Parts requiring ductility and high strength
- Parts requiring high corrosion resistance

Heat Treatment Options

- Annealed: 1900°F for 2 hours in a vacuum
- H900: Hardens part at 900°F in argon for 1 hour
- H1150: Anneals part at 1150°F in argon for 4 hours
- Heat Treatment 1: HIP + AMS 5604

TYPICAL PHYSICAL PROPERTIES

MECHANICAL PROPERTIES	AMS 5604/5643 (MIN REQ.)	TYPICAL WROUGHT	DMLS (AS BUILT)	DMLS (HT1)	DMLS (HIP)	DMLS (ANNEALED)
0.02% Yield	-	-	106 ksi	180 ksi	119 ksi	103 ksi
Ultimate Tensile	-	-	151 ksi	211 ksi	166 ksi	175 ksi
Elongation	-	-	17%	11%	12%	12%
Hardness	-	-	~ 30 HRC	-	-	-

STAINLESS STEEL 17-4 PH COMPOSITION

ELEMENT	TYPICAL PERCENTAGE
Carbon (C)	0.07 max
Manganese (Mn)	1.00 max
Phosphorus (P)	0.040 max
Sulfur (S)	0.030 max
Silicon (Si)	1.00 max
Chromium (Cr)	15.00 - 17.50
Nickel (Ni)	3.00 - 5.00
Copper (Cu)	3.00 - 5.00
Niobium plus Tantalum (Cb, Ta)	0.15 - 0.45

The information presented represents typical values intended for reference and comparison purposes only. It should not be used for design specifications or quality control purposes. End-use material performance can be impacted (+/-) by, but not limited to, part design, end-use conditions, test conditions, color etc. Actual values will vary with build conditions. Product specifications are subject to change without notice. *Chemical analysis for specific lots available upon request.

The performance characteristics of these materials may vary according to application, operating conditions, or end use. Each user is responsible for determining that the material is safe, lawful, and technically suitable for the intended application. Stratasys makes no warranties of any kind, express or implied, including, but not limited to, the warranties of merchantability, fitness for a particular use, or warranty against patent infringement.