



Somos® ProtoGen 18420

Tough, high impact stereolithography material that you can tailor to fit your needs.

Description

When you need a high-heat and humidity resistant material for your parts, Somos® ProtoGen 18420 delivers the performance you need. This material creates accurate, easy-to-clean white parts, ideal for automotive and medical applications.

Benefits

- Tune the properties of the part to fit your needs
- Fast, easy processing & finishing
- Highly accurate

Applications

- Automotive parts
- Medical
- Consumer Products
- Electrical casings

Somos® ProtoGen 18420 Technical Data

Liquid Properties		Optical Properties		
Appearance	White	E_c	6.7 m/cm ²	[critical exposure]
Viscosity	~350 cps @ 30°C	D_p	4.3 mils	[slope of cure-depth vs. ln (E) curve]
Density	~1.16 g/cm ³ @ 25°C	E_{10}	68.6 m/cm ²	[exposure that gives 0.254 mm (.010 inch) thickness]

Mechanical Properties		UV Postcure	
ASTM Method	Property Description	Metric	Imperial
D638M	Tensile Modulus	2,250 MPa	326 ksi
D638M	Tensile Strength at Yield	43 MPa	6.2 ksi
D638M	Elongation at Break	12%	
D2240	Flexural Modulus	2,060 MPa	299 ksi
D256A	Izod Impact (Notched)	21 J/m	0.39 ft-lb/in
D2240	Hardness (Shore D)	87	
D570-98	Water Absorption	0.68%	

Thermal/Electrical Properties		UV Postcure	
ASTM Method	Property Description	Metric	Imperial
E831-05	C.T.E. -40 - 0°C (-40 - 32°F)	75 $\mu\text{m}/\text{m}^\circ\text{C}$	42 $\mu\text{in}/\text{in}^\circ\text{F}$
E831-05	C.T.E. 0 - 50°C (32 - 122°F)	106 $\mu\text{m}/\text{m}^\circ\text{C}$	59 $\mu\text{in}/\text{in}^\circ\text{F}$
E831-05	C.T.E. 50 - 100°C (122 - 212°F)	125 $\mu\text{m}/\text{m}^\circ\text{C}$	70 $\mu\text{in}/\text{in}^\circ\text{F}$
E831-05	C.T.E. 100 - 150°C (212 - 302°F)	134 $\mu\text{m}/\text{m}^\circ\text{C}$	74 $\mu\text{in}/\text{in}^\circ\text{F}$
D150-98	Dielectric Constant 60 Hz	3.6	
D150-98	Dielectric Constant 1 KHz	3.5	
D150-98	Dielectric Constant 1 MHz	3.2	
D149-97A	Dielectric Strength	14 V/mm	355 V/mil
D648	HDT @ 0.46 MPa (66 psi)	96°C	205°F

These values may vary and depend on individual machine processing and post-curing practices.

DSM Functional Materials Somos® Material Group

in North America

1122 St. Charles Street
Elgin, Illinois 60120
USA
Phone: +1.847.697.0400

in Europe

Slachthuisweg 30
3151 XN Hoek van Holland
The Netherlands
Phone: +31.174.315.391

in China

476 Li Bing Road
Zhangjiang Hi-Tech Park
Pudong New Area
Shanghai 201203, China
Phone: +86.21.6141.8064

Visit us online at www.dsm.com/somos

NOTICE: Somos® is a registered trademark of Royal DSM N.V. Somos® is an unincorporated subsidiary of DSM Desotech Inc. The information presented herein is based on generally accepted analytical and testing practices and is believed to be accurate. However, DSM Desotech expressly disclaims any product warranties which may be implied including warranties of merchantability and/or fitness for a particular purpose. DSM Desotech's products are sold subject to DSM Desotech's standard terms and conditions of sale, copies of which are available upon request. Purchasers are responsible for determining the suitability of the product for its intended use and the appropriate manner of utilizing the product in purchaser's production processes and applications so as to insure safety, quality and effectiveness. Purchasers are further responsible for obtaining necessary patent rights to practice any invention in connection with the use of purchased product and any other product or process. DSM Desotech reserves the right to change specifications of their products without notice.

© 2016 DSM IP ASSETS B.V. All rights reserved.
032016 | SOMOS-ProtoGen 18420_Stratagis Direct